

CORODUR® 864

CORODUR® 864 is a flux cored wire, which produces a heat and thermal shock resistant deposit. The wire is designed for maintenance of hot working tools and to increase their service life. The number of layers can be done as

necessary. The interpass temperature should be maximum 250°C. The alloyed weld deposit has excellent properties of resistance to impact. The weld deposit is still well machinable.



TYPICAL ALL WELD METAL ANALYSIS (%)

Basis = Fe

C	Si	Mn	Cr	Mo	V	W	Ti
0,25	0,7	0,6	5,0	1,5	0,4	1,4	0,2

Hardness HRC 44-48,5

Tensile strength N/mm² 1400-1600*

* machinable

HOT FORGING MOLDS

PARAMETER

Diameter	Voltage	Amps
1,6	22-26	180-240
2,4	25-27	260-300
2,8	26-28	280-340

Other dimensions on request

FORMS OF DELIVERY

Unit	Weight
Coil BS 300	15 kg
Coil B 450	25 kg
Drums	300 kg

G = Gas shielded